

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>C09D</b>	<b>A2</b>	(11) International Publication Number: <b>WO 96/23030</b> (43) International Publication Date: 1 August 1996 (01.08.96)
<p>(21) International Application Number: PCT/US96/00987</p> <p>(22) International Filing Date: 24 January 1996 (24.01.96)</p> <p>(30) Priority Data: 08/377,660 25 January 1995 (25.01.95) US</p> <p>(71) Applicant: NORTHERN ENGRAVING CORPORATION [US/US]; 803 South Black River Street, Sparta, WI 54656 (US).</p> <p>(72) Inventors: CRARY, Kevin, E.; 218 South 20th Street, LaCrosse, WI 54601 (US). PETERS, Arnis, E.; 803 South Black River Street, Sparta, WI 54656 (US).</p> <p>(74) Agent: SHIFLEY, Charles, W.; Banner &amp; Allegretti, Ltd., Ten South Wacker Drive, Chicago, IL 60606 (US).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>Without international search report and to be republished upon receipt of that report.</i></p>
<p>(54) Title: IMPROVED FLUORESCENT INKS</p> <p>(57) Abstract</p> <p>A fluorescent ink comprises, as primary constituents, long-wave activated inorganic phosphor pigment and acrylic resin, with the ink being fluorescent under long-wave ultraviolet radiation. As preferred, the fluorescent ink further comprising visible-light activated pigment, and the acrylic resin is transparent to long-wave ultraviolet radiation. Also as preferred, the inorganic phosphor is rare-earth doped, and there are additives selected from among the group of flow agent, foam suppressants, and surfactants. As most preferred, the fluorescent ink comprises a mixture of long-wave activated, rare-earth doped, inorganic phosphor pigment, visible-light activated pigment, and acrylic resin at least partially transparent to long-wave radiation, with the proportion of visible-light activated pigment and the proportion of phosphor pigment relative to each other being established to provide fluorescence of the ink. The ink is screen-printable, the pigments having particle sizes less than 15 microns, and the phosphor pigment is selected from among the group comprising red, green and blue phosphor pigments, the proportions of the red, green and blue phosphor pigments relative to each other being established to provide desired color of fluorescence of the ink. Still further, the phosphor pigment is photostable, white body color pigment, inert to moisture, and selected from among the group comprising <math>Y_2O_3S:Eu</math>, <math>Zn_2GeO_4:Mn</math>, and <math>BaMg_2Al_{16}O_{77}:Eu</math>. A fluorescent display device comprises a long-wave ultraviolet light source and a display panel, with the panel imprinted with the described fluorescent ink.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Ghana	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

**IMPROVED FLUORESCENT INKS****BACKGROUND OF THE INVENTION**

This invention relates to automotive display panels, such as dashboard panels, and more particularly to the constructions by which such panels are made visible at night.

5 Automotive display panels, where "automotive" connotes cars, trucks, motorcycles, and vehicles generally, currently are formed of materials such as clear polycarbonate. The clear polycarbonate is decorated front and back for day and night-time displays. The decoration  
10 on the front includes daytime information, on a background, typically black. The daytime information is formed of pigmented inks, screen printed on the panels in desired colors, typically white. The decoration on the back of the panels includes nighttime information, again in pigmented  
15 inks, provided to be visible through the panel under back lighting. Decoration on the panel backs allows nighttime colors such as red and green to be different from daytime white.

Compensation is also printed on the panel back. This  
20 compensation allows substantially equal brightness across the panel under back lighting, even though the back lighting may be uneven. As an example, some panels are back lit from the side. Further, warning displays, known as telltales, are provided, to be visible under  
25 illumination of warning lights.

Automotive display panels as described are the standard of the automotive industry, given the rigorous performance standards of that industry. Panels as described are a desirable combination of materials able to  
30 survive automotive quality control requirements at affordable pricing. Such quality control requirements include temperature testing for survival in hostile, steady-state heat and freezing; hostile temperature cycling; sustained high humidity; sustained intense

lighting; and combinations of lighting, temperature, humidity, and water spray.

This standard of the industry is not without deficiencies and costs. As an example, as indicated, 5 compensation is required for adequately uniform back lighting. However, despite deficiencies and costs, alternative panels and lighting schemes are not known to the commercial automotive industry. Among other schemes not known, fluorescent displays are not known. A variety 10 of patents disclose fluorescent lighting of indicia such as automotive instrumentation information, but the inventions of such patents have not been adopted in commercial applications. Inability to satisfy quality control requirements at competitive pricing is believed to be the 15 primary reason for the lack of adoption. Use of ultraviolet lighting which is unsuitable to close proximity to drivers and passengers is believed to further contribute to the situation.

**SUMMARY OF THE INVENTION**

An object, then, of the present invention, is to provide fluorescent displays for automotive instrumentation which satisfy quality control requirements at competitive  
5 pricing.

Another object is to provide fluorescent lighting which avoids lighting unsuitable for the intended application.

These and other objects are satisfied in an invention  
10 which, in a principal aspect, takes the form of a fluorescent display device which comprises a long-wave ultraviolet light source and a display panel. The panel is imprinted with a fluorescent ink display, the ink including long-wave activated inorganic phosphor pigment, and acrylic  
15 resin. The ink is fluorescent under long-wave ultraviolet radiation. The ultraviolet light source is positioned relative to the display panel to illuminate the display with long-wave ultraviolet light, from the front. In more particular embodiments, the ink of the fluorescent display  
20 has all the particular features described hereafter.

In another principal aspect, the present invention takes the form of a specific fluorescent ink. The invented ink comprises, as primary constituents, long-wave activated inorganic phosphor pigment and acrylic resin, with the ink  
25 being fluorescent under long-wave ultraviolet radiation. As preferred, the fluorescent ink further comprises visible-light activated pigment, and the acrylic resin is transparent to long-wave ultraviolet radiation. Also as preferred, the inorganic phosphor is rare-earth doped, and  
30 there are additives selected from among the group of flow agents, foam suppressants, and surfactants.

As most preferred, the fluorescent ink comprises a mixture of long-wave activated, rare-earth doped, inorganic phosphor pigment, visible-light activated pigment, and  
35 acrylic resin at least partially transparent to long-wave radiation, with the proportion of visible-light activated pigment and the proportion of phosphor pigment relative to each other being established to provide fluorescence of the

ink. The ink is screen-printable, the pigments having particle sizes less than 15 microns, and the phosphor pigment is selected from among the group comprising red, green and blue phosphor pigments, the proportions of the red, green and blue phosphor pigments relative to each other being established to provide desired color of fluorescence of the ink. Still further, the phosphor pigment is photostable, white body color pigment, inert to moisture, and selected from among the group comprising  $Y_2O_3S:Eu$ ,  $Zn_2GeO_4:Mn$ ,  $BaMg_2Al_{16}O_{77}:Eu$  and  $3(Ba,Mg)O \cdot 8Al_2O_3:Eu$ ,  $Mn$ . The light source emits 340 to 380, and most preferably 365, nanometer light.

The ink of the invention is printed on the face of the invented display panels. Only telltales are printed on the back of the panels. All other back printing is eliminated. Back lighting is eliminated. Satisfying illumination levels are obtained in ambient light, and in ultraviolet light. Multiple applications of different inks, to gain desirable daytime displays and desirable nighttime displays, are unnecessary. Color changes between day and night are possible, and may even include color "flips" between white and virtually any desired color. Refined displays are also possible, as sizes of pointers and informational markings are adapted to the ink of the invention.

The full range of objects, aspects and advantages of the invention are only fully understood by a reading of the detailed description of the preferred embodiments of the invention. That description follows.

**BRIEF DESCRIPTION OF THE DRAWING**

The preferred embodiments of the invention will be described in relation to the accompanying drawing. The drawing includes figures, as follows:

5      FIG. 1 is a perspective view of a typical automotive display panel, decorated according to the invention, with a central portion broken away to reveal internal detail.

FIG. 2 is a cross-section view of an automotive display panel according to the invention and as in FIG. 1.

**DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT**

Referring to Figures 1 and 2, the preferred embodiment of the present invention includes both a fluorescent ink for a display device, and a display device comprising  
5 fluorescent ink.

In a preferred display as in Figure 1, a panel 10 such as an automotive instrument display panel incorporates indicia 12 and a background 14. As most preferred, both the background 14 and indicia 12 are on a polycarbonate  
10 substrate. The background 14 is black ink, and the indicia 12 are formed according to the invention with inks comprising resin, phosphor pigments, and transparent pigments. The transparent pigments supply colors to the indicia under ambient, daytime lighting, and the phosphor  
15 pigments supply colors to the indicia under ultraviolet lighting. Less preferred, available substrates include acrylic, aluminum, polyester and the like.

Referring to Figures 1 and 2 both, a display device 16 incorporates the panel 10 in combination with additional  
20 elements, to form an instrument panel suitable for day and nighttime operation of a car. A viewing panel 18, such as a formed sheet of clear plastic, defines a surface near an observer, such as an automobile operator (i.e., a driver).

A space 20 exists behind the panel 18, which defines  
25 the interior of the display device 16. A rear wall 22, and surrounding top, bottom and side walls complete the definition of the interior 20. As necessary, working elements such as a speedometer needle 23 extend into the space 20.

30 The display panel 10 is mounted on or comprises the rear wall 22 of the display device 16. As above, the display panel 10 incorporates indicia 12 formed of inks comprising daytime and fluorescent pigments. An ultraviolet light source 24, such as a black light tube,  
35 extends along the bottom of the interior space 20, inside a reflector housing 26. The light source 24 emits 340 to 380, and most preferably 365, nanometer light, under the control of the driver, through the operation of a switch

(not shown). Thus, as desired, the driver may actuate the light source 24 as needed, typically at night.

Referring again to Figure 2, the light source 24 is in front of the display panel 10, where "in front of" has the meaning of the light source being positioned proximate the face of the display panel 10, i.e., on the "side" of the display panel nearer the observer, i.e., the driver. As shown, the light source 24 may be offset laterally to the bottom, top, or side of the panel 10, while remaining in front of the panel 10.

Ultraviolet light from the source 24 radiates off the source 24, onto the panel 10. Radiation may be direct, if so desired, but is preferred to be indirect. Louvers 27 may be, and most preferably are, interposed between the light source 24 and panel 10, and prevent direct radiation of light from the source 24 onto the panel 10. Alternately, light from the source 24 reflects onto the housing 26, which incorporates a reflective surface 28. Light also radiates onto the inner surface of the viewing panel 18, which itself reflects light onto the panel 10, as represented by arrows 29. Light finally radiates to an opposed reflective surface 30, opposite the light source 24 across the span of the display panel 10, and thereby onto the panel 10, as represented by arrow 31.

All of the reflective surface 28, viewing panel 18, and opposed reflective surface 30 are angled, arranged and composed to reflect ultraviolet light onto the display panel 10, and thereby the indicia 12. In the daytime, in ambient light, the indicia 12 are visible on the background as a result of the daytime pigments of the indicia's ink. At night, under the light of the ultraviolet source 24, the indicia 12 fluoresce, and are visible as fluorescent, as ultraviolet light reflects off the fluorescent pigments of the ink. Because the source 24 emits low intensity, 365 manometer light, night viewing is safe and vivid.

An ink according to the present invention incorporates a resin, preferably an acrylic resin. A particularly desired resin is available from Summit Screen Inks, of

North Kansas City, Missouri, as K-89510 Plas-Tec Clear resin. K-89510 Plas-Tec Clear resin is a formulation of K-85541 Plas-Tec Mixing Clear resin, without flow agents or bubble breaker additives. K-89510 is also a proprietary  
5 blend of Summit Screen Inks, of acrylic resins, without any substantial vinyl modification or alkyd modification. K-89510 Plas-Tec Clear Resin has a manufacturing viscosity of Z1-Z2 Gardner Holdt (bubble type) and a density of 8.3 pounds per gallon. While the identified resin is  
10 preferred, as is acrylic resin, it is believed possible to employ epoxies, urethanes and acrylic resins, although vinyl modified or alkyd modified resins are not, at this time, considered to be suitable.

Daytime color pigments may be added to the resin, as  
15 are phosphors and additives. Preferred daytime color pigments are transparent pigments. These pigments are "transparent" in that they pass 365 nanometer ultraviolet light. Desirable transparent pigments are available from Summit Screen Inks as K-85530, 31, 32, 33, 34, 35, 36 37,  
20 38, 39, 40, 74 and 75 Plas-Tec Ink Toners. All the identified pigments have excellent light fastness.

Preferred phosphor pigments ("phosphors") are also added to the resin. Preferred phosphors are photostable, white in body color, and inert to moisture. Most  
25 preferred  $Y_2O_3S:Eu$ ,  $Zn_2GeO_4:Mn$ ,  $BaMg_2Al_{16}O_{27}:Eu$  and  $3(Ba,Mg)O \cdot 0.8Al_2O_3:Eu, Mn$ . Less preferred are  $ZnO:Zn$ ,  $Sr_2(PO_4)_2Cl:Eu$  and  $Y_2O_3S:Eu$ . These phosphors are "white in body color" in that they exhibit a milky white appearance in ambient light. Under ultraviolet light,  $Y_2O_3S:Eu$  is red,  
30  $Zn_2GeO_4:Mn$  is green,  $BaMg_2Al_{16}O_{27}:Eu$  is blue, and  $3(Ba,Mg)O \cdot 0.8Al_2O_3:Eu, Mn$  is also green.

Whether daytime color pigments are to be added is a matter of choice, dependent on the daytime color desired for the ink and the resulting display. In the absence of  
35 daytime color pigments, the white body color of the phosphors gives the indicia 12 a white appearance. Where daytime color pigments are desired, to achieve a particular daytime color, the color co-ordinates of the desired color

are identified --using a color-coordinate scheme which plots colors on a color space, such as CIE 1931, and assigns co-ordinates to the colors-- and combinations of daytime color pigments are added to achieve the desired co-ordinates. As necessary, spectrophotometry is used to identify the color co-ordinates of the resin-pigment mixture resulting from a first combination of resin and daytime color pigment(s), and iteration between pigment addition and spectrophotometric analysis is used to correct the resin-pigment mixture to the desired daytime color. Phosphor pigments are added to the resin system in a preferred proportion of 4-6 parts total phosphor to 4 parts resin system. Excess phosphor results in a paste, while excess resin results in an undesirable graininess of phosphor. Intuitively, the proportions of phosphor to resin system are believed to range suitable between 3:7 and 3:1 parts of resin system to parts of phosphor. The desired proportions of 4:6 resin to phosphor is believed to provide a most desirable combination of workability and nighttime brightness.

As with the daytime pigments, the phosphor pigments may be combined to achieve a specific desired phosphor color. The color co-ordinates of the desired color are identified. Using 365 nanometer black light, an estimate of the combination of red, blue and green phosphors necessary to achieve these color co-ordinates, and the combination, with resin, is created. The color is examined by spectrophotometry and as necessary, iteration between spectrophotometry and pigment combination is used to achieve the desired color. Only one green is used, in combination with a red and a blue, to achieve desired color. Of the two preferred green phosphors, the green is chosen which permits achievement of desired color. Where possible,  $\text{Zn}_2\text{GeO}_4\text{:Mn}$  is used. As preferred, the process is aided by the technique known as the designed experiment technique, as explained, for example, in the test "Design of Experiments", the computer program XStat of the publisher Wiley, and "How To Run Mixture Experiments for

Product Quality" by John A. Cornell, Am. Soc. for Q.C., Statistics Division, Milwaukee, Wisconsin, 1990. Also as most preferred, the spectrophotometer utilized is a Photo Research model 704, and analysis occurs in a darkroom.

5       As above, without daytime pigments, daytime color is white. Added daytime pigments result in a daytime color which may be the same as, or different from nighttime fluorescent color. Limitations of such color "flips" result from daytime pigments shifting the emissive,  
10 nighttime color toward the daytime color. A non-white daytime color and a white nighttime color are not thought to be possible in combination.

With resin and pigments, i.e., inks, as provided, where particle size is held to less than 15 microns, all  
15 indicia 12 to be created can be created by screen printing. Alternatives to screen printing, such as pad printing, dip coating and the like are also viable. With a panel which is to have some fluorescent markings and some non-fluorescent markings, or fluorescent markings of differing  
20 colors, multiple screen printings are suitable. All decoration is accomplished, however, on a single surface, or otherwise as desired. Unlike past display decorations, back surface decoration for any nighttime graphics may be eliminated.

25       The described phosphors are readily combined with resin through mixing, with slow addition of phosphor during stirring with a high speed disperser.

The preferred embodiment, and the manner of making and using it, are now described. To particularly point out and  
30 distinctly claim the subject matter regarded as invention, the following claims conclude this specification. Numerous variations in the specific details of the invention and its application will be understood to be within the spirit and scope of the invention and the claims.

## CLAIMS

What is claimed is:

1. A fluorescent ink comprising:  
long-wave activated inorganic phosphor pigment; and  
acrylic resin;  
the ink being fluorescent under long-wave ultraviolet  
5 radiation.
2. A fluorescent ink as in claim 1 further  
comprising visible-light activated pigment.
3. A fluorescent ink as in claim 1 or claim 2  
wherein the acrylic resin is transparent to long-wave  
ultraviolet radiation.
4. A fluorescent ink as in claim 1 or 2 wherein the  
inorganic phosphor is rare-earth doped.
5. A fluorescent ink as in claim 1 or 2 further  
comprising additives selected from among the group of flow  
agents, foam suppressants, and surfactants.
6. A fluorescent ink, comprising a mixture of the  
following:  
long-wave activated, rare-earth doped, inorganic phosphor  
pigment;  
5 visible-light activated pigment; and acrylic resin at  
least partially transparent to long-wave radiation; the ink  
being fluorescent under long-wave ultraviolet radiation.
7. A fluorescent ink as in claim 6, the proportion  
of visible-light activated pigment and the proportion of  
phosphor pigment relative to each other being established  
to provide fluorescence of the ink.
8. A screen-printable fluorescent ink as in claim 6,  
the pigments having particle sizes less than 15 microns.

9. A fluorescent ink as in claim 6, the phosphor pigment being selected from among the group comprising red, green and blue phosphor pigments, the proportions of the red, green and blue phosphor pigments relative to each other being established to provide desired color of fluorescence of the ink.

10. A fluorescent ink as in claim 6, the phosphor pigment being photostable pigment.

11. A fluorescent ink as in claim 6, the phosphor pigment being white body color pigment.

12. A fluorescent ink as in claim 6, the phosphor pigment being pigment inert to moisture.

13. A fluorescent ink as in claim 6, the phosphor pigments being selected from among the group comprising  $Y_2O_3S:Eu$ ,  $Zn_2GeO_4:Mn$ , and  $BaMg_2Al_{16}O_{27}:Eu$ .

14. A fluorescent display device comprising:  
a long-wave ultraviolet light source; and  
a display panel, the panel imprinted with a display, the display imprinted by fluorescent ink, the ink including long-wave activated inorganic phosphor pigment, and acrylic resin, the ink being fluorescent under long-wave ultraviolet radiation;  
the light source positioned relative to the display panel to illuminate the display with long-wave ultraviolet light.

15. A fluorescent display device as in claim 14, the ink further comprising visible-light activated pigment.

16. A fluorescent display device as in claim 14 wherein the acrylic resin of the ink is transparent to

long-wave ultraviolet radiation.

17. A fluorescent display device as in claim 14 wherein the inorganic phosphor of the ink is rare-earth doped.

18. A fluorescent display device as in claim 14 wherein the ink further comprises additives selected from among the group of flow agents, foam suppressants, and surfactants.

19. A fluorescent display device as in claim 14, the ink comprising a mixture of long-wave activated, rare-earth doped, inorganic phosphor pigment, visible-light activated pigment, and acrylic resin at least partially transparent  
5 to long-wave radiation, the ink being fluorescent under long-wave ultraviolet radiation.

20. A fluorescent display device as in claim 19, the proportion of visible-light activated pigment and the proportion of phosphor pigment relative to each other being established to provide fluorescence of the ink.

21. A fluorescent display device as in claim 19, the ink being screen-printable fluorescent ink, the pigments having particle sizes less than 15 microns.

22. A fluorescent display device as in claim 19, the

phosphor pigment of the ink being selected from among the group comprising red, green and blue phosphor pigments, the proportions of the red, green and blue phosphor pigments relative to each other being established to provide desired  
5 color of fluorescence of the ink.

23. A fluorescent display device as in claim 19, the phosphor pigment being photostable pigment.

24. A fluorescent display device as in claim 19, the phosphor pigment of the ink being white body color pigment.

25. A fluorescent display device as in claim 19, the phosphor pigment of the ink being pigment inert to moisture.

26. A fluorescent ink as in claim 19, the phosphor pigments of the ink being selected from among the group comprising  $Y_2O_3S:Eu$ ,  $Zn_2GeO_4:Mn$ , and  $BaMg_2Al_{16}O_{27}:Eu$ .

1/1





Fig. 2



**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C09D 11/10, G09F 13/20</b>	<b>A3</b>	<b>(11) International Publication Number:</b> <b>WO 96/23030</b> <b>(43) International Publication Date:</b> 1 August 1996 (01.08.96)
<b>(21) International Application Number:</b> PCT/US96/00987 <b>(22) International Filing Date:</b> 24 January 1996 (24.01.96)  <b>(30) Priority Data:</b> 08/377,660 25 January 1995 (25.01.95) US  <b>(71) Applicant:</b> NORTHERN ENGRAVING CORPORATION [US/US]; 803 South Black River Street, Sparta, WI 54656 (US).  <b>(72) Inventors:</b> CRARY, Kevin, E.; 218 South 20th Street, LaCrosse, WI 54601 (US). PETERS, Arnis, E.; 803 South Black River Street, Sparta, WI 54656 (US).  <b>(74) Agent:</b> SHIFLEY, Charles, W.; Banner & Allegretti, Ltd., Ten South Wacker Drive, Chicago, IL 60606 (US).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>  <b>(88) Date of publication of the international search report:</b> 26 September 1996 (26.09.96)
<b>(54) Title:</b> FLUORESCENT INK AND FLUORESCENT DISPLAY DEVICE  <b>(57) Abstract</b>  A fluorescent ink comprises, as primary constituents, long-wave activated inorganic phosphor pigment and acrylic resin, with the ink being fluorescent under long-wave ultraviolet radiation. A fluorescent display device comprises a long-wave ultraviolet light source and a display panel, with the panel imprinted with the described fluorescent ink.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 96/00987

## A. CLASSIFICATION OF SUBJECT MATTER

C 09 D 11/10.G 09 F 13/20

According to International Patent Classification (IPC) or to both national classification and IPC <sup>6</sup>

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C 09 D,G 09 F,B 60 Q,C 09 K,B 60 K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP, A, 0 273 997 (INCAS INTERNATIONAL CARBON SOLVENT) 13 July 1988 (13.07.88), claims.	1
A	--- DATABASE WPIL, no. 94-072 128, DERWENT PUBLICATIONS LTD., London; & JP.A,06 025 584 (NIPPON KEIKO KAGAKU KOGYO KK et al.), abstract. -----	1

☐ Further documents are listed in the continuation of box C.

☐ Patent family members are listed in annex.

### \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*&\* document member of the same patent family

Date of the actual completion of the international search  
14 June 1996

Date of mailing of the international search report

29.07.96

Name and mailing address of the ISA

European Patent Office, P.O. 5818 Patenusaan 2  
NL - 2280 HV Rijswijk  
Tel.: (31-70) 340-2040, Fax: 31 631 epo nl.  
Telex: (31-70) 340-3016

Authorized officer

PAHMEIGER e.r.l.

# ANHANG

zum internationalen Recherchen-  
bericht über die internationale  
Patentanmeldung Nr.

# ANNEX

to the International Search  
Report to the International Patent  
Application No.

# ANNEXE

au rapport de recherche inter-  
national relatif à la demande de brevet  
international n°

PCT/US 96/00987 SAE 126457

In diesem Anhang sind die Mitglieder  
der Patentfamilien der im obenge-  
nannten internationalen Recherchenbericht  
angeführten Patentdokumente angegeben.  
Diese Angaben dienen nur zur Unter-  
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family  
members relating to the patent documents  
cited in the above-mentioned inter-  
national search report. The Office is  
in no way liable for these particulars  
which are given merely for the purpose  
of information.

La présente annexe indique les  
membres de la famille de brevets  
relatifs aux documents de brevets cités  
dans le rapport de recherche inter-  
national visé ci-dessus. Les renseigne-  
ments fournis sont donnés à titre indica-  
tif et n'engagent pas la responsabilité  
de l'Office.

In Recherchenbericht angeführtes Patentdokument Patent document cited in search report Document de brevet cité dans le rapport de recherche	Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
EP A2 273997		EP TD 273997	23-05-90
		JP A2 63175089	19-07-88
		AU A1 11771/88	17-08-89
		DK A0 450/88	29-01-88
		OK A 450/88	30-07-89
		FI A0 8806355	11-02-88
		FI A 8806355	12-08-89
		NO A0 880617	11-02-88
		AU B2 607463	07-03-91
		FI B 88051	15-12-92
		FI CC 88051	25-03-93
		NO A 880617	14-08-89

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**